

Test Result(s):

Colour fastness to laundering

Method: ISO 105-C06:2010. Test No. A15, machine wash at 40°C with 4g/l 'ECE(B)' detergent with 10 steel balls.

Material No.	Test Item	Client's Requirement (Min. Grade)	Results (Grade)	Conclusion
1	Colour change	4	4-5	PASS
	Colour stain on	--		
	Acetate	3-4	3-4	
	Cotton	3-4	4-5	
	Nylon	3-4	4	
	Polyester	3-4	4-5	
	Acrylic	3-4	4-5	
	Wool	3-4	4-5	

Note:**Explanation of Colour fastness Results**

Negligible or no change or staining

Slightly changed or stained

Noticeably changed or stained

Considerably changed or stained

Much changed or heavily stained

Fabric Weight

Method: ISO 3801-1977ⁿ Method 5

Material No.	Client's Requirement (g/m ²)	Results (g/m ²)	Conclusion
1	209±5%	211	PASS