

**Test Result:**

Appearance of apparel and other textile end products after repeated home laundering

Method: AATCC 143-2018 <sup>s</sup>

Test Procedure: Test No. (1)(II)(Ai), Machine wash at 27°C(80°F) with 1.8kg(4lb) loading, normal cycle, tumble dry low, turn inside out.

Observation on washed sample: after 5 washes.

<b>Material No.</b>	<b>Test Item</b>	<b>Client's Requirement (Min. Grade)</b>	<b>Results (Grade)</b>	<b>Conclusion</b>
1	Fabric smoothness	SA- 3.5	SA- 4.0	PASS

**Notes:****Smoothness Appearance Grade By SA Replica Equivalents**

- SA-5 Equivalent to the SA-5 Replica. Very smooth, pressed, finished appearance.
- SA-4 Equivalent to the SA-4 Replica. Smooth, finished appearance.
- SA-3.5 Equivalent to the SA-3.5 Replica. Fairly smooth but non-pressed appearance.
- SA-3 Equivalent to the SA-3 Replica. Mussed, non-pressed appearance.
- SA-2 Equivalent to the SA-2 Replica. Rumpled, obviously wrinkled appearance.
- SA-1 Equivalent to the SA-1 Replica. Crumpled, creased and severely wrinkled appearance.